

NR Quick Dry Films

Type of Films	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	E	UF	TSER
NR Charcoal QD 05	1.0 Mil	6%	6%	45%	7%	48%	<1%	93%	0.67	0.85	1.12	42%
NR Charcoal QD 20	1.0 Mil	20%	6%	48%	6%	46%	<1%	78%	0.69	0.86	1.15	40%
NR Charcoal QD 30	1.0 Mil	30%	6%	52%	6%	42%	<1%	67%	0.73	0.86	1.14	36%
NR Charcoal QD 40	1.0 Mil	38%	6%	55%	6%	39%	<1%	58%	0.76	0.86	1.14	34%
NR Charcoal QD 50	1.0 Mil	51%	6%	60%	7%	33%	<1%	44%	0.80	0.86	1.14	31%
NR Charcoal QD 70	1.0 Mil	70%	7%	70%	9%	21%	<1%	23%	0.87	0.86	1.13	24%

- T : Thickness ● VLT : Visible Light Transmittance ● VLR : Visible Light Reflectance ● SET : Solar Energy Transmittance
- SER : Solar Energy Reflectance ● SEA : Solar Energy Absorbance ● UVT : Ultra Violet Transmittance ● GR : Glare Reduction
- SC : Shading Coefficient ● E : Emissivity ● UF : U Factor (BTU /HR./SQ.FT.) ● TSER : Total Solar Energy Rejection